

Latex Free

Non Sterile

HAKUZO Powder Free NITRILE ESS GLOVES ESS 200 pcs

Well fitting nitrile gloves with high chemical resistance and elasticity

Made from latex-free material. Can be used by latex allergy users.



Hakuzo Medical Corporation



Product Features

- •High stretchablility provides superior fit and comfort.
- •Non-stock and anti-slip coatings give better handling.
- •High chemical resistance.
- Made of latex-free material, can be used by latex allergy users.
- Powder free gloves minimise the risk of contamination from powder splash.



(Material)
Nitrile Rubber

Specifications

Size	Full Length	Palm Width
XS	240mm ±10mm	75mm ±5mm
S	240mm ±10mm	85mm ±5mm
М	240mm ±10mm	95mm ±5mm
L	240mm ±10mm	110mm ±5mm

Quality Standards

Pinhole

AQL1.5

Chemotherapy Drugs Permeation Testing

The following tests are based on the standard of ASTM D6978-05.

Test Method	Chemotheropy Drugs	Concentration	Breakthrough Detection Time	
ASTM D 6978-05	Methotrexate	25.0mg/ml (25,000 ppm)	No breakthrough up to 240 minutes	
	CDDP	1.0mg/ml (1,000ppm)		
	СРА	20.0mg/ml (20,000ppm)		
	Dacarbazine	10.0mg/ml (10,000ppm)		
	Doxorubincin hydrochloride	2.0mg/ml (2,000ppm)		
	Etoposide	20.0mg/ml (20,000ppm)		
	5-fluorouracil	50.0mg/ml (50,000ppm)		
	Paclitaxel	6.0mg/ml (6,000ppm)		
	Vincristine sulfate	1.0mg/ml (1,000ppm)	-	
	Mitomycin c	0.5mg/ml (500ppm)		

Chemical Resistance Test

The following test is based on the standard of EN374-3.

Test Method	Chemical	Concentration	Breakthrough Detection Time
EN374-3:2003	Sodium hydroxide	40%	No breakthrough up to 480 minutes





Add: 2-4-9, Tokuicho, Chuo-ku, Osaka 540-0025, Japan TEL: 06-6942-0451 FAX: 06-6945-0539 www.hakuzo.co.jp/eng/index.php